

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09J 7/02	A1	(11) International Publication Number: WO 94/09079 (43) International Publication Date: 28 April 1994 (28.04.94)
(21) International Application Number: PCT/US93/10082 (22) International Filing Date: 21 October 1993 (21.10.93) (30) Priority data: 964,167 21 October 1992 (21.10.92) US (71) Applicant: ALLIED-SIGNAL INC. [US/US]; 101 Columbia Road, P.O. Box 2245, Morristown, NJ 07962-2245 (US). (72) Inventors: YANKUS, Edward, Victor ; 19 Wall Street, Hoosick Falls, NY 12090 (US). HAMILTON, Robert, Francis ; 318 Turnpike Road, Eagle Bridge, NY 12057 (US). (74) Agent: FUCHS, Gerhard, H.; Allied-Signal Inc., Law Department (C.A. McNally), 101 Columbia Road, P.O. Box 2245, Morristown, NJ 07962-2245 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: PLASMA SPRAY MASKING TAPE (57) Abstract A masking tape for use in masking a part in a high velocity oxy-fuel (HVOF) plasma spray process. The tape is formed from a fabric which is tightly woven from yarns of aramid fibers. A silicone rubber impregnates the inner fabric layer. First and second silicone rubber layers are coated onto opposite sides of the impregnated fabric. A pressure-sensitive adhesive is coated on to the second silicone rubber layer, which is preferably laminated with a release liner.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	FR	France	MR	Mauritania
AU	Australia	GA	Gabon	MW	Malawi
BB	Barbados	GB	United Kingdom	NE	Niger
BE	Belgium	GN	Guinea	NL	Netherlands
BF	Burkina Faso	GR	Greece	NO	Norway
BG	Bulgaria	HU	Hungary	NZ	New Zealand
BJ	Benin	IE	Ireland	PL	Poland
BR	Brazil	IT	Italy	PT	Portugal
BY	Belarus	JP	Japan	RO	Romania
CA	Canada	KP	Democratic People's Republic of Korea	RU	Russian Federation
CF	Central African Republic	KR	Republic of Korea	SD	Sudan
CG	Congo	KZ	Kazakhstan	SE	Sweden
CH	Switzerland	LI	Liechtenstein	SI	Slovenia
CI	Côte d'Ivoire	LK	Sri Lanka	SK	Slovak Republic
CM	Cameroon	LU	Luxembourg	SN	Senegal
CN	China	LV	Latvia	TD	Chad
CS	Czechoslovakia	MC	Monaco	TC	Togo
CZ	Czech Republic	MG	Madagascar	UA	Ukraine
DE	Germany	ML	Mali	US	United States of America
DK	Denmark	MN	Mongolia	UZ	Uzbekistan
ES	Spain			VN	Viet Nam
FI	Finland				

PLASMA SPRAY MASKING TAPE

5 Background of the Invention

Field of the Invention

This invention related to a flame spray tape to mask articles during a plasma spray process.

10 Description of the Prior Art

Plasma or flame spraying of parts is a known technique for applying a protective metal or ceramic coating to the part. Such process provides a thermal spray coating over the part by bringing the metal or ceramic to the melting point and spraying on a surface to produce a thin coating. Plasma spray coating typically is achieved using a plasma gun or similar device.

In the plasma spray process, it is important to mask certain areas of the parts in order to prevent application of the coating. Reasons for masking parts include preventing the coating from entering apertures in the part, maintaining dimensions within a critical range, weight savings and the like. To achieve such masking, a masking tape is applied over the areas in which the coating is not desired.

The masking tape must exhibit excellent thermal and abrasion - resistance, both in protecting adjacent surfaces from the grit blasting that is typically used as a surface preparation and the actual plasma spray coating. Such tape must not lift off or fray during this demanding process and are designed to quickly and easily release from the part surface without leaving an adhesive residue.

35 Conventional plasma spray tapes typically include a glass fabric which is impregnated with a silicone adhesive and which is coated with a high temperature

-2-

silicone pressure sensitive adhesive. A release liner is usually employed for convenient handling. Other types of masking tapes include a thin aluminum foil laminated to a fiber glass cloth.

5 Although such masking tapes are effective with the typical plasma spray process, they are not effective with a recently introduced, more demanding process known as a high velocity oxy-fuel (HVOF) process. This process is a continuous combustion process in which the
10 spray gun is essentially a rocket in which the powder is injected into the exhaust stream. The exhaust stream is exiting at hypersonic speed (several thousand feet per second).

 It would be desirable to provide an improved
15 plasma spray masking tape which will withstand the extremely demanding HVOF process.

SUMMARY OF THE INVENTION

 In accordance with this invention, there is
20 provided a masking tape for use in masking against a high velocity oxy-fuel plasma spray process, the masking tape comprising:

- (a) an inner fabric layer formed of tightly woven yarns of aramid fibers;
- 25 (b) a silicone rubber impregnating the inner fabric layer;
- (c) a first silicone rubber layer coated on a first face of the impregnated inner fabric layer;
- (d) a second silicone rubber layer coated on a
30 second face of the impregnated inner fabric layer; and
- (e) a silicone pressure-sensitive adhesive coated onto the second silicone rubber layer.

-3-

DESCRIPTION OF THE PREFERRED EMBODIMENTS

The masking tape of this invention is useful in a high velocity oxy-fuel (HVOF) plasma spray process.

5 The tape has an internal fabric layer which is tightly woven from aramid fibers. A preferred fabric layer is a woven aramid fabric available under the trademark Kevlar. Preferably, the yarns have a substantially flat cross-section, and the fabric is woven in a plain
10 weave, although other weaves may be employed.

As mentioned above, the fabric employed in this invention is woven from aramid fiber yarns in a tightly woven pattern. This reduces the open spaces between
15 the overlapping yarns. Preferably, the fabric has a thread count of from about 20 x 20 to about 30 x 30 (per inch). The fabric preferably is a relatively light weight fabric which has a weight of from about 1.5 to about 5 ounces/square yard. The thickness of
20 the fabric may range, for example, from about 3 to about 10 mils.

The fabric layer is impregnated with a silicone rubber, which may be accomplished in any suitable
25 manner. Preferably, the silicone rubber is applied by a dip coating and metering process and the fabric is dried in a drying oven. The silicone rubber employed is a liquid having a low viscosity and is typically formed by mixing and blending a two component system.
30 The viscosity of the mixed material typically may be in the range of about 15,000 to about 35,000 cps. The silicone rubber preferably is a material which is a platinum-catalyzed addition reaction product. The fabric is impregnated with the silicone rubber such
35 that the entire fabric is within a silicone rubber

-4-

matrix. The silicone rubber may extend beyond the fabric's outer surfaces to any desired amount.

After the aramid fabric is impregnated with the
5 silicone rubber, a layer of silicone rubber is coated
onto one side of the impregnated aramid fabric.
Preferably, the side that is coated first is the front
side of the fabric, i.e., the side that faces the
plasma spray in use. The silicone rubber employed as
10 the coating layer preferably is the same type of
silicone rubber that is used to impregnate the aramid
fabric. The silicone rubbers employed in this
invention are also referred to as silicone elastomers.

15 The coating of the silicone rubber layer onto the
impregnated aramid fabric layer can be performed using
any suitable technique. Preferably, the silicone
rubber coating is applied by a horizontal knife over
roll coater and the coated fabric is dried in a drying
20 oven.

The thickness of the first coating layer (on the
back side of the fabric) may range from about 5 to
about 20 mils, preferably from about 12 to about 16
25 mils.

The impregnated aramid fabric is then coated on
its opposite face, also with a silicone rubber. Again,
any suitable coating technique can be employed.
30 Preferably, the same type of coating apparatus that is
used to coat the front side of the fabric is also used
to coat the opposite side.

The thickness of the second coating layer is
35 generally thinner than that of the first coating, and

-5-

may range from about 3 to about 20 mils, preferably about 6 to about 10 mils.

5 It may be possible to apply both the first and second coatings at the same time to opposite sides of the fabric. In each coating step, an appropriate drying operation is employed.

10 A silicone pressure-sensitive adhesive layer is coated onto the exterior of the second silicone rubber layer. Any suitable silicone adhesive may be employed. Preferred is a high temperature di-phenyl silicone adhesive. The adhesive layer is preferably applied by a reverse roll coater and is dried in a drying oven.
15 Typically, the thickness of the silicone adhesive layer is about 3 to about 10 mils, preferably about 4 to about 7 mils.

20 A release liner is preferably laminated to the silicone adhesive layer in a conventional manner. The release liner may be any liner that is typically used for silicone pressure-sensitive adhesives.

25 Preferably, a primer layer is coated onto the exterior face of the second silicone rubber coating before the adhesive layer is applied, in order to promote adhesion of the adhesive to the silicone rubber. The primer may be another silicone layer, which may be applied as a relatively thin layer (such
30 as on order of less than about 0.5 mils).

As mentioned above, the masking tape of this invention finds suitability to mask HVOF plasma sprayed parts. In such process, the tape must be able to
35 withstand high impact at temperatures in the range of

-6-

above about 500°F (260°C). It is believed that the aramid fabric layer provides increased strength, flexibility and abrasion resistance to the masking tape structure. The impregnated silicone adhesive is
5 believed to also improve the abrasion resistance of the construction. In addition, the use of the silicone layer beneath the fabric is believed to provide impact resistance so as to cushion the impact of the spray particles, thereby allowing the fabric to absorb more
10 energy from the spray.

The HVOF plasma spray tape of the present invention can be applied to mask an object for spraying in a simplified process. This is in contrast to the
15 expensive and time-consuming previously employed system in which a metal tool is designed and made to mask the object to be coated. In addition, the masking tape of this invention can be used to make the coating of irregularly shaped objects possible.

20

-7-

WHAT IS CLAIMED IS:

1. A masking tape for use in masking against a high velocity oxy-fuel plasma spray process, said masking
5 tape comprising:
 - (a) an inner fabric layer formed of tightly woven yarns of aramid fibers;
 - (b) a silicone rubber impregnating said inner fabric layer;
 - 10 (c) a first silicone rubber layer coated on a first face of said impregnated inner fabric layer;
 - (d) a second silicone rubber layer coated on a second face of said impregnated inner fabric layer; and
 - (e) a silicone pressure-sensitive adhesive coated
15 onto said second silicone rubber layer.
2. The masking tape of claim 1, further comprising a release liner laminated to said silicone pressure-sensitive adhesive.
20
3. The masking tape of claim 1, wherein said fabric layer is a woven from substantially flat aramid yarns.
- 25 4. The masking tape of claim 3, wherein said woven fabric has a plain weave.
5. The masking tape of claim 1, wherein said first silicone rubber layer has a thickness of from
30 about 5 to about 20 mils.
6. The masking tape of claim 5, wherein said second silicone rubber layer has a thickness of from about 3 to about 20 mils.

-8-

7. The masking tape of claim 1, further comprising a primer layer interposed between said second silicone rubber layer and said pressure-sensitive adhesive.

5

8. The masking tape of claim 1, wherein said first silicone rubber layer is thicker than said second silicone rubber layer.

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 93/10082

A. CLASSIFICATION OF SUBJECT MATTER
IPC 5 C09J7/02 B32B25/20

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C09J B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	DATABASE WPI Week 9241, Derwent Publications Ltd., London, GB; AN 92-335746 & JP,A,4 239 578 (POLYMER HIGASHI NIPPON KK) 27 August 1992 see abstract ---	1
A	US,A,4 636 427 (SHOJI OHNO) 13 January 1987 see abstract ---	1
A	GB,A,1 072 891 (PRECISION RUBBERS LD.) 21 June 1967 see claims 1,2 -----	1,2

☐ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents:

- "A" document defining the general state of the art which is not considered to be of particular relevance
"E" earlier document but published on or after the international filing date
"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
"O" document referring to an oral disclosure, use, exhibition or other means
"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

29 March 1994

Date of mailing of the international search report

19. 04. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Girard, Y

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/US 93/10082

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
US-A-4636427	13-01-87	JP-B- 1041189 JP-C- 1614728 JP-A- 61118483	04-09-89 15-08-91 05-06-86
GB-A-1072891		NONE	